

# TR6075

# DNP

All Purpose Resin



TR6075 is an all purpose resin that prints at high speeds, up to 12 IPS, while maintaining high barcode and image quality. TR6075's superior chemical and abrasion resistance make it the perfect choice for general or demanding applications.

## Specific Features

- Produces excellent barcodes and variable images at higher speeds
- Higher durability than most resins on the market with greater solvent resistance
- Compatible with a vast array of substrates
- UL recognized
- Superior ability to dissipate static
- Heat resistance up to 170°C

## Recommended Applications

Shelf labels, warning labels, tamper-evident labeling, drum labels, jewelry tags, component labels, automotive labels, CD and DVD spine labels.



### Jewelry Tags

DNP ribbons offer scratch-resistant images on many preprinted or treated label stocks.



### Pharmaceutical Labels

DNP ribbons provide dark, durable images for critical applications.



### Shelf Labels

Clear, crisp DNP printed images are easily seen and read in retail applications.



### Warning Labels and Signs

Exceptional long-term durability of DNP images satisfy industrial and outdoor sign requirements.



Registered to  
ISO 9001

Visit us at [www.dnpribbons.com](http://www.dnpribbons.com)

# TR6075

All Purpose Resin

## Ribbon Property

Description	Specification	Measurement Method
Ink Material	Resin	—
Total Thickness (µm)	8.7 ± 0.8	Micrometer
Base Film Thickness (µm)	4.5 + 0.4	Micrometer
Ink Thickness (µm)	1.4 ± 0.4	Micrometer
Ribbon Transmission Density	> 1.15	Densitometer
Print Density	> 1.6	Densitometer

## Durability of Printed Image

Label Stock: Top Coated White Polyester	
Print Speed: 8 IPS	Print Density: 2.40
Smudge Resistance: ANSI A1	Scratch Resistance: ANSI A1
Highly resistant to rubbing with Formula 409 and mineral spirits.	
Test Equipment: Colorfastness Tester	
Conditions: Smudge Test: 100 cycles @ 800 grams with cotton cloth	
Scratch Test: 100 cycles @ 380 grams with 3mm diameter steel ball	
<sup>1</sup> Represents the American National Standard Institute (ANSI) Grade measured at the given conditions. Grade levels are A, B, C, D, and F, where A is excellent, B is above average, C is average, D is below average, and F is poor.	

## Conversion Chart

Millimeters (mm) to inches = mm ÷ 25.4	Inches to mm = Inches ÷ 0.03937
Meters (m) to Feet (ft) = m ÷ 0.3048	Feet to Meters = Feet ÷ 3.2808
C° to F° = (1.8 x C°) + 32 = F°	F° to C° = (F° ÷ 1.8) - 17.77 = C°
Thousand square inches (MSI) to m <sup>2</sup> = msi x 0.645	MSI = m <sup>2</sup> ÷ 0.645

## Recommended Applications

Shelf labels, warning labels, tamper-evident labeling, drum labels, jewelry tags, component labels, automotive labels, CD and DVD spine labels.

The information on this data sheet was obtained in DNP IMS America laboratories. Measured values may vary slightly when tested in a different environment. Information contained within this document is subject to change without notification.

**DNP IMS America Corporation**  
 1001 Technology Drive  
 Mt. Pleasant, PA 15666-1766  
 Phone: 724-696-7500  
 FAX: 724-696-7555  
 E-mail: sales\_marketing@dnpribbons.com

Visit us at [www.dnpribbons.com](http://www.dnpribbons.com)  
 6075 7/08